

ARTICLE

Received 12 Mar 2013 | Accepted 26 Jun 2013 | Published 25 Jul 2013

DOI: 10.1038/ncomms3204

Chemical influence on β -relaxations and the formation of molecule-like metallic glasses

Hai Bin Yu¹, Konrad Samwer¹, Wei Hua Wang² & Hai Yang Bai²

Secondary (also known as Johari-Goldstein or β -) relaxations are an intrinsic feature of supercooled liquids and glasses. They are important in many respects but the underlying mechanisms are not well understood. A long-standing puzzle is why some glasses show β -relaxations as pronounced peaks, whereas others as unobvious excess wings. Here we demonstrate that these different behaviours are related to the fluctuations of chemical interactions by using prototypical systems of metallic glasses. A general rule is summarized: pronounced β -relaxations are associated with systems where all the atomic pairs have large similar negative values of enthalpy of mixing, whereas positive or significant fluctuations in enthalpy of mixing suppress β -relaxations. The emerging physical picture is that strong and comparable interactions among all the constituting atoms maintain string-like atomic configurations for the excitations of β -events and can be considered as the formation of molecule-like metallic glasses.

¹I. Physikalisches Institut, Universität Göttingen, D-37077 Göttingen, Germany. ²Institute of Physics, Chinese Academy of Sciences, Beijing 100190, China. Correspondence and requests for materials should be addressed to K.S. (email: ksamwer@gwdg.de)

Supercooled liquids and glasses display diverse relaxation dynamics^{1–6}. In addition to the primary (α -) relaxations that are responsible for the viscous flow, a kind of secondary relaxation, called Johari-Goldstein or β -relaxation^{7–9}, often exists at high frequencies or low temperatures. Recent studies have demonstrated that β -relaxations are an intrinsic and universal feature of supercooled liquids and glasses^{1,8,10}, and they are of significance to the understanding of many key issues in glassy physics and material sciences¹, ranging from glass transition phenomenon^{10–13}, diffusions^{14–17}, physical aging^{18,19} to mechanical properties^{20,21} and mechanisms of plastic deformations^{21–23}, as well as the stabilities and crystallization of glassy materials^{24–26}.

Despite their importance, the behaviour of β -relaxation themselves are not well understood, as they seem to be system dependent and even more complex than α -relaxations^{1,5}. In some supercooled liquids and glasses, β -relaxations manifest as distinct peaks in dielectric or mechanical loss spectra. In some other systems, β -relaxations appear to be absent and, instead, excess contributions to the tails of α -relaxations show up⁵. These so-called excess wings have been observed in many systems without well-resolved peaks of β -relaxations. Historically, excess wings and peaks of β -relaxations were considered as two different phenomena and the corresponding materials were defined as type A- and B-glass formers, respectively⁵. Now it is commonly recognized they are similar in nature and excess wings are due to underlying β -relaxations^{1,8,13,27,28}. However, a basic question remains unclear: why do some glasses exhibit pronounced peaks of β -relaxation, whereas others display excess wings? This question fundamentally connects to the structural origin of β -relaxations, which is also a long-standing unsolved question in glassy physics. As these two issues are interrelated, a thorough investigation of the former could provide deeper insights of the latter, and *vice versa*. On the other hand, to understand the dominating factors that govern the behaviours of β -relaxation are of practical importance. For example, polymers and MGs with pronounced β -relaxations at relatively low temperatures (for example, below or near room temperature) usually exhibit good ductility and they are favoured for mechanical applications^{20,21}. However, for the pharmaceuticals industry, β -relaxations are sometimes undesired and should be suppressed as they cause the devitrification and destabilization of glassy medicines, which have better solubility and bioavailability than their crystalline counterparts^{1,10,24,25}.

MGs have recently received a lot of attention as model systems for studying β -relaxations because of their rich phenomenology in relaxation behaviours, simple atomic structures compared with other glasses (for example, polymers and molecular glasses) and widely tunable compositions^{13–15,21,22,29}. However, it is noted that studying β -relaxations in MGs is much more difficult than that in molecular and polymer glasses⁸.

In this work, by systematic scrutiny of the composition-dependent β -relaxations in several prototypical systems of MGs, we show a strong chemical effect on the behaviours of β -relaxation. A general rule is summarized, that is, the behaviours of β -relaxations are correlated to the fluctuations of the chemical interactions among the constituting atoms. Specifically, pronounced β -relaxations are always associated with MGs that all the atomic pairs have large similar negative values of enthalpy of mixing and the difference among these values should be small; however, positive enthalpy of mixing or a large difference in the enthalpy of mixing suppresses β -relaxations. We interpreted these findings in terms of recent theoretical ideas³⁰, that string-like excitations are essential for β -events. The implications of this result for the understanding of structural origins of β -relaxations in MGs are discussed. The obtained insights provide a practical guideline for controlling β -relaxations in MGs and have implications for other type of glasses.

Results

La-based MGs. Figure 1a–c show the temperature T -dependent loss modulus E'' (measured from dynamical mechanical analyser; see the Methods section) of the three MG systems in a normalized frame, where T and E'' are scaled by the glass transition temperature T_g and $E''(T = T_g)$, respectively. For clarity, curves only with testing frequency $f = 1$ Hz are displayed. Figure 1a illustrates the effect of Cu substitution of Ni atoms on the behaviours of relaxation in the $\text{La}_{70}(\text{Cu}_x\text{Ni}_{1-x})_{15}\text{Al}_{15}$ MGs. For the Cu-free $\text{La}_{70}\text{Ni}_{15}\text{Al}_{15}$ MG, besides the usual α -relaxation around T_g , a pronounced E'' peak is observed in the temperature range $0.6–0.8 T_g$, corresponding to the β -relaxation in the deep glassy state. With the increasing concentration of Cu to replace Ni atoms, the peaks of β -relaxation shift gradually to higher-scaled temperatures and become less pronounced. Eventually,




Figure 1 | Behaviours of β -relaxations in MGs. The normalized plot of E'' as a function of T_g scaled temperature of (a) $\text{La}_{70}(\text{Cu}_x\text{Ni}_{1-x})_{15}\text{Al}_{15}$ MGs with four different x values as indicated; (b) $\text{Pd}_{40}\text{Ni}_{10}\text{Cu}_{30}\text{P}_{20}$ and $\text{Pd}_{40}\text{Ni}_{40}\text{P}_{20}$ MGs; and (c) $(\text{Cu}_{0.5}\text{Zr}_{0.5})_{100-x}\text{Al}_x$ MGs with four different x values as indicated.

β -relaxation in the Ni-free $\text{La}_{70}\text{Cu}_{15}\text{Al}_{15}$ MG manifests as a shallow shoulder on the low-temperature tail of α -relaxation. As Ni and Cu have nearly the same atomic sizes but different electron configurations ($3d^8 4s^2$ and $3d^{10} 4s^1$, respectively), the above result indicates a strong chemical effect on the behaviours of β -relaxations—in the $\text{La}_{70}(\text{Cu}_x\text{Ni}_{1-x})_{15}\text{Al}_{15}$ MGs, Cu suppresses β -relaxations making them less pronounced, whereas Ni promotes them.

Pd-based MGs. The effect of Ni/Cu on the behaviours of β -relaxation in $\text{Pd}_{40}(\text{Cu}_x\text{Ni}_{1-x})_{40}\text{P}_{20}$ MGs is presented in Fig. 1b. For the Cu-free $\text{Pd}_{40}\text{Ni}_{40}\text{P}_{20}$ MG, its β -relaxation manifests as a weak shoulder that superimposed on the tail of α -relaxation. Replacing Ni by Cu atoms in this system makes β -relaxations more pronounced and separated from α -relaxations (shift to lower-scaled temperatures). This observation demonstrates again a strong chemical effect on the behaviours of β -relaxation; however, in contrast to the $\text{La}_{70}(\text{Cu}_x\text{Ni}_{1-x})_{15}\text{Al}_{15}$ system shown in Fig. 1a, Cu promotes β -relaxations in the $\text{Pd}_{40}(\text{Cu}_x\text{Ni}_{1-x})_{40}\text{P}_{20}$ system. Such a comparison indicates the effect of Ni/Cu on the behaviours of β -relaxation is not solely determined by their atomic properties but dependent on their specific chemical environments and the interactions with other constituting atoms. This is different from some other properties of MGs. For example, the elastic modulus of MGs can be approximated by a simple 'rule-of-mixture'³¹ and largely determined by the main constituting elements³². For the considerations of glass-forming ability, Ni and Cu are even sometimes regarded as same^{33,34}. Distinctively, we note the mechanical behaviours (especially, the ductility and toughness) of MGs are sensitive to chemical effects^{35,36}, in agreement with the notion that mechanical properties and β -relaxations are correlated^{21,22}.

CuZr-based MGs. Fig. 1c shows the effects of Al alloying in a $(\text{Cu}_{0.5}\text{Zr}_{0.5})_{100-x}\text{Al}_x$ MG system. For the Al-free $\text{Cu}_{50}\text{Zr}_{50}$ MG, its β -relaxation manifests a weak but discernable shoulder, whereas a minute amount of Al alloying (about 4%) drastically suppresses the

shoulder and an excess wing shows up instead. With further alloying of Al, the excess wings persist and become more closely merged with α -relaxations. This result demonstrates microalloying has important influence on the behaviours of β -relaxation as well.

Discussion

All these findings above demonstrate a strong and complicated (system specific) chemical effect on the behaviours of β -relaxation in MGs. A pertinent question is how to understand these system-specific behaviours in a general physical scenario. To appreciate this question, we consider the concept of enthalpy of mixing for MGs as it provides an effective way to the understanding of many chemical-related issues in MGs, such as glass-forming ability^{33,34}, mechanical properties³⁷, phase separation^{38–40}, as well as crystallization and devitrification of MGs⁴¹. Fig. 2a–c display the values of enthalpy of mixing $\Delta H_{AB}^{\text{mix}}$, for different atomic pairs in these three prototypical MG systems³⁴. They are obtained from Miedema's model for binary alloys (with equiatomic composition, $\text{A}_{50}\text{B}_{50}$)^{34,42}, which is a semi-quantitative theory based on the thermodynamics of materials and energy band theory. We first evaluated the mean chemical affinity ΔH^{chem} for these MGs. As suggested in Takeuchi *et al.*³⁴ and He *et al.*³⁵, the ΔH^{chem} of a given multicomponents alloy can be estimated using a weighted average approach, $\Delta H^{\text{chem}} = 4 \sum_{A \neq B} \Delta H_{AB}^{\text{mix}} c_A c_B$ (where c_A and c_B are the molar percentage of the elements A and B, respectively). Figure 2d shows the ΔH^{chem} as a function of $x = (\text{Cu}/(\text{Cu} + \text{Ni}))$ for the $\text{La}_{70}(\text{Cu}_x\text{Ni}_{1-x})_{15}\text{Al}_{15}$ and $\text{Pd}_{40}(\text{Cu}_x\text{Ni}_{1-x})_{40}\text{P}_{20}$ MG-systems. It is observed all the compositions in both systems have large negative values of ΔH^{chem} in the range of -20 to -30 kJ mol^{-1} . The largest negative values of ΔH^{chem} are found at composition points of $\text{La}_{70}\text{Ni}_{15}\text{Al}_{15}$ and $\text{Pd}_{40}\text{Cu}_{40}\text{P}_{20}$ for the two systems, respectively, and interestingly both of the compositions show pronounced β -relaxations. The dependence of ΔH^{chem} against x is also correlated with the compositional-dependent behaviours of β -relaxation in these two systems, which seems to indicate a trend that the larger negative values of ΔH^{chem} the more pronounced β -relaxations. However, we find this observation is not applicable




Figure 2 | Enthalpy of mixing and mean chemical affinity of MGs. The enthalpy of mixing for the constituting atomic pairs in (a) La-Ni-Cu-Al (b) Pd-Ni-Cu-P and (c) Zr-Cu-Al systems; and the compositional-dependent mean chemical affinity ΔH^{chem} for (d) $\text{La}_{70}(\text{Cu}_x\text{Ni}_{1-x})_{15}\text{Al}_{15}$ and $\text{Pd}_{40}(\text{Cu}_x\text{Ni}_{1-x})_{40}\text{P}_{20}$ MGs and (e) $(\text{Cu}_{0.5}\text{Zr}_{0.5})_{100-x}\text{Al}_x$ MGs. The units in a–c are kJ mol^{-1} . Dash-dot ellipses in a,b indicate compositions with pronounced β -relaxations; arrows in d,e indicate the directions along which β -relaxations become more pronounced with composition variations in each systems.

to the $(\text{Cu}_{0.5}\text{Zr}_{0.5})_{100-x}\text{Al}_x$ systems. As shown in Fig. 2e with microalloying of Al, the ΔH^{chem} becomes more negative but β -relaxation becomes less pronounced (cf. Fig. 1c), which is opposite to the expectation from that of $\text{La}_{70}(\text{Cu}_x\text{Ni}_{1-x})_{15}\text{Al}_{15}$ or $\text{Pd}_{40}(\text{Cu}_x\text{Ni}_{1-x})_{40}\text{P}_{20}$. These results imply (i) large negative values of ΔH^{chem} might be a necessary condition but not sufficient to guarantee pronounced β -relaxations; (ii) although the correlation between ΔH^{chem} and the behaviours of β -relaxation are interesting and useful for the La- and Pd-based MGs, it is system specific and thus not universal (at least not suitable for Cu-Zr-Al MGs); (iii) and there must be other underlying influential factors that govern the behaviours of β -relaxation beyond the ‘mean-field’-like approach to the mean chemical affinity.

We next take into account of the fluctuations of chemical interactions. A closer examination of $\Delta H_{\text{AB}}^{\text{mix}}$ for these different atomic pairs shown in Fig. 2a–c reveals the following clue. In systems with pronounced β -relaxations, all the atomic pairs have large negative and comparable values of $\Delta H_{\text{AB}}^{\text{mix}}$, whereas systems with positive enthalpy of mixing or large difference in the enthalpy of mixing are associated with less pronounced β -relaxations or excess wings. For instance, in the La-Ni-Al system with pronounced β -relaxations, the $\Delta H_{\text{AB}}^{\text{mix}}$ for La-Ni, La-Al and Ni-Al atomic pairs are -28 , -37 and -22 kJ mol^{-1} , respectively, whereas in the La-Cu-Al system with less pronounced β -relaxations, $\Delta H_{\text{AB}}^{\text{mix}}$ for Al-Cu is -1 kJ mol^{-1} , much smaller than that for other two atomic pairs (-21 and -37 kJ mol^{-1} for La-Cu and La-Al atomic pairs, respectively), and thus there is a large difference in enthalpy of mixing between different atomic pairs. This finding is also applicable to Pd-Cu/Ni-P and Zr-Cu-Al systems as shown in Fig. 2b,c respectively.

We have verified that above finding also holds in other 12 ternary MG systems (see Table 1), including RE-TM-Al (where RE = La, Pr, Nd, Sm, Gd and Er; TM = Co, Ni and Cu; their β -relaxations are pronounced peaks for TM = Co and Ni and shoulders for TM = Cu), Zr-Cu-Ag (excess wings), Cu-Ti/Zr-Be (excess wings), Pt-Cu/Ni-P (humps) and Pd-Cu-Si (humps). One exception is observed in La/Ce-Cu-Al systems^{8,43} where La-Cu-Al MGs have shoulder-like β -relaxations, whereas in Ce-Cu-Al MGs excess wings even La and Ce have the similar values of enthalpy of mixing with Cu and Al. This may be explained by the different electronic structures between La and Ce that are not accounted by the enthalpy of mixing from Miedema’s model. As the Miedema’s model is only empirical estimates, to obtain accurate values of enthalpy of mixing in a particular system, experiments or first-principle calculations are required. Besides, the values of enthalpy of mixing might even be concentration dependent. Furthermore, we caution that the approach of enthalpy of mixing does not consider the interactions between the same kinds of atoms, which could be important for binary or monatomic systems and systems with high concentrations of solvent atoms. Nevertheless, as the above systems are different in many respects and cover most of the known MGs, our findings thus indicate that both of the magnitude and fluctuations of chemical interactions among constituting atoms are influential factors to the behaviours of β -relaxation in MGs. Specifically, strong and comparable interactions among all the constituting atoms, which might be viewed as the local formation of molecule-like structures, are favourable for pronounced β -relaxations, otherwise for excess wings. These findings are compatible with a coupling model^{1,9}, which suggests stronger interactions are beneficial for pronounced β -relaxations.

Recently, a theoretical work predicts β -relaxation is related to the excitations of string-like configurations³⁰, and a subsequent molecular dynamics simulation corroborated it⁴⁴. Accordingly, a β -event is considered as a chain of atoms that moves back-and-

Table 1 | β -relaxation characteristics and enthalpy of mixing.

No.	MG system	β -relaxation	$\Delta H_{\text{AB}}(\text{kJ mol}^{-1})$
1	La-Ni-Al	Peaks	$\Delta H_{\text{La-Ni}} = -27$
			$\Delta H_{\text{La-Al}} = -38$
			$\Delta H_{\text{Ni-Al}} = -22$
2	La-Cu-Al	Shoulders	$\Delta H_{\text{La-Cu}} = -21$
			$\Delta H_{\text{La-Al}} = -38$
			$\Delta H_{\text{Cu-Al}} = -1$
3	La-Co-Al	Peaks	$\Delta H_{\text{La-Co}} = -17$
			$\Delta H_{\text{La-Al}} = -38$
			$\Delta H_{\text{Co-Al}} = -19$
4	Sm-Co-Al	Peaks	$\Delta H_{\text{Sm-Co}} = -22$
			$\Delta H_{\text{Sm-Al}} = -38$
			$\Delta H_{\text{Co-Al}} = -19$
5	Ce-Cu-Al	Excess wings	$\Delta H_{\text{Ce-Cu}} = -21$
			$\Delta H_{\text{Ce-Al}} = -38$
			$\Delta H_{\text{Cu-Al}} = -1$
6	Ce-Ni-Al	Peaks/humps	$\Delta H_{\text{Ce-Ni}} = -28$
			$\Delta H_{\text{Ce-Al}} = -38$
			$\Delta H_{\text{Ni-Al}} = -22$
7	Pd-Cu-P	Humps	$\Delta H_{\text{Pd-Cu}} = -14$
			$\Delta H_{\text{Pd-P}} = -37$
			$\Delta H_{\text{Cu-P}} = -18$
8	Pd-Ni-P	Shoulders	$\Delta H_{\text{Pd-Ni}} = 0$
			$\Delta H_{\text{Pd-P}} = -37$
			$\Delta H_{\text{Ni-P}} = -35$
9	Pt-Ni-P	Shoulders	$\Delta H_{\text{Pt-Ni}} = -5$
			$\Delta H_{\text{Pt-P}} = -35$
			$\Delta H_{\text{Ni-P}} = -35$
10	Pt-Cu-P	Humps	$\Delta H_{\text{Pt-Cu}} = -12$
			$\Delta H_{\text{Pt-P}} = -35$
			$\Delta H_{\text{Cu-P}} = -18$
11	Cu-Zr-Be	Excess wings	$\Delta H_{\text{Cu-Zr}} = -23$
			$\Delta H_{\text{Cu-Be}} = 0$
			$\Delta H_{\text{Zr-Be}} = -43$
12	Cu-Ti-Be	Excess wings	$\Delta H_{\text{Cu-Ti}} = -9$
			$\Delta H_{\text{Cu-Be}} = 0$
			$\Delta H_{\text{Ti-Be}} = -30$
13	Pd-Cu-Si	Humps	$\Delta H_{\text{Pd-Cu}} = -14$
			$\Delta H_{\text{Pd-Si}} = -55$
			$\Delta H_{\text{Cu-Si}} = -19$
14	Cu-Zr-Ag	Excess wings	$\Delta H_{\text{Cu-Zr}} = -23$
			$\Delta H_{\text{Cu-Ag}} = 2$
			$\Delta H_{\text{Zr-Ag}} = -20$
15	Zr-Cu-Al	Excess wings	$\Delta H_{\text{Zr-Cu}} = -23$
			$\Delta H_{\text{Zr-Al}} = -44$
			$\Delta H_{\text{Cu-Al}} = -1$
16	Zr-Ni-Al	Humps	$\Delta H_{\text{Zr-Ni}} = -49$
			$\Delta H_{\text{Zr-Al}} = -44$
			$\Delta H_{\text{Ni-Al}} = -22$

β -relaxation, Johari-Goldstein relaxation; MG, metallic glass.

The β -relaxations as measured by dynamical mechanical spectroscopy in different MG systems and the enthalpy of mixing among their constituting atoms. The elements are arranged from high to low concentrations in each MG system.

forth reversibly and cooperatively within the confinement of surrounding elastic matrix^{14,45}. In light of this scenario, it is reasonable that strong and comparable magnitudes of interactions among all the constituting atoms are necessary for archiving a critical length for the string-like atomic configurations for the movements of β -events, whereas weak interactions (or large fluctuations) between certain atomic pairs would break the string-like configurations, making them less cooperative. Presumably, weakly bonded atoms diffuse readily, and thus acting as ‘cutters’ or ‘anti-glue’ to the string. In other words, we suggest strong interactions hold neighbouring atoms together to form the string-like configurations and to complete cooperative

β -events. We noted that maintaining a certain length of atomic/molecular chains has been inferred critical to the behaviours of β -relaxations in different types of glasses. For example, Mattsson *et al.*⁴⁶ studied the chain length-dependent relaxations in a series $\text{CH}_3\text{O}[\text{CH}_2\text{CH}(\text{CH}_3)\text{O}]_n\text{CH}_3$ organic glasses. By varying the chain length $n = 1, 2, 3$ and ≈ 7 and in a polymer ($n \approx 69$), they found in dielectric spectra for $n \leq 3$ β -relaxations manifest as excess wings, whereas a broad hump for $n \approx 7$, and a distinct peak for the polymer ($n \approx 69$). A similar result was observed in polyalcohols by Döbß *et al.*⁴⁷ These findings suggest that shortening the chain structures could suppress β -relaxations (other possible reasons are also noted in Ngai *et al.*⁴⁸). In Pd-Ni-Cu-P MG systems, several studies from the electronic and atomic structural perspectives have uncovered that with the increasing of Cu contents, the MGs acquire deeper binding energy and develop more covalent-like bonding, and especially chain-like Pd-P-Pd/Cu atomic configuration was suggested^{49–51}. These findings are consistent with our observation that Cu promotes β -relaxations in Pd-Ni/Cu-P systems because of its strong interactions with Pd and P. In a Pd-Cu-Si MG, Bedorf and Samwer⁴⁵ studied the length-scale effects on relaxations and they found that by reducing the film thickness < 30 nm, the β -relaxations are effectively suppressed. This result was explained because of the breakdown of the stress field surrounding the string-like excitation when free surfaces are reached and the pinning effects of free surface⁴⁵. More recently, Casalini *et al.*⁵² used $-\text{SCH}_3$ to replace $-\text{OCH}_3$ group in poly(methyl methacrylate) and they found in dielectric spectra that the intensity of the β -relaxation is substantially reduced, as the result of the electronegativity of sulphur is much less than that of oxygen⁵². Their observations demonstrated that tuning the chemical interactions can result in different behaviours of β -relaxation in polymers, similar with our findings in MGs. These results, together with our present findings, seem to suggest string-like motions of molecule-like structures are a universal mechanism of β -relaxation in glassy materials, ranging from MGs, molecular and polymer glasses.

In summary, we identified an influential chemical effect on the behaviours of β -relaxations in MGs—large similar negative enthalpy of mixing among all the constituting atoms results in pronounced β -relaxation peaks in mechanical loss spectra, whereas positive or large fluctuations in the values of enthalpy of mixing suppress β -relaxations and usually associate with excess wings. The behaviour of β -relaxations is proposed to correlate with a characteristic length scale of string configurations. Our findings provide a practical guideline in controlling the behaviour of β -relaxations in MGs and have implications for other type of glasses as well.

Methods

Sample preparation. Three typical MG systems with 10 different compositions were selected for experiments; these are $\text{La}_{70}(\text{Cu}_x\text{Ni}_{1-x})_{15}\text{Al}_{15}$ with $x = 0, 0.5, 0.67$ and 1; $\text{Pd}_{40}(\text{Cu}_x\text{Ni}_{1-x})_{40}\text{P}_{20}$ with $x = 0$ and 0.75; and $(\text{Cu}_{0.5}\text{Zr}_{0.5})_{100-x}\text{Al}_x$ with $x = 0, 4, 8$ and 10, respectively; because of their markedly different relaxation behaviours that are representative for most known MGs. The La-based and CuZr-based MGs are prepared by Cu-mold casting method: the raw materials were melted in a Ti-gettered argon atmosphere and subsequently cast into a water-cooled Cu-mold. The Pd-based MGs (with P containing) were prepared by induction melting of the raw materials in argon-filled and sealed quartz tube, additional B_2O_3 were used as fluxing medium. The fluxed alloys were then re-melted and cast by Cu-mold casting method.

Characterization. The glassy nature of the samples was ascertained by X-ray diffraction (a MAC Mo3 XHF diffractometer with Cu K_α radiation and a Bruker D8 with Cu K_α radiation) and differential scanning calorimeter (PerkinElmer DSC-7 and DSC-5). The dynamical mechanical spectroscopies of these MGs were measured on a TA Q800 dynamical mechanical analyser by single-cantilever bending method with a heating rate of 2 K min^{-1} , strain amplitude about 0.1% and discrete testing frequency of 1, 2, 4, 8, 16 and 32 Hz.

References

- Ngai, K. L. *Relaxation and Diffusion in Complex Systems* (Springer, 2011).
- Ediger, M. D. & Harrowell, P. Perspective: supercooled liquids and glasses. *J. Chem. Phys.* **137**, 080901–080915 (2012).
- Angell, C. A., Ngai, K. L., McKenna, G. B., McMillan, P. F. & Martin, S. W. Relaxation in glass-forming liquids and amorphous solids. *J. Appl. Phys.* **88**, 3113–3157 (2000).
- Dyre, J. C. Colloquium: the glass transition and elastic models of glass-forming liquids. *Rev. Mod. Phys.* **78**, 953–972 (2006).
- Lunkenheimer, P., Schneider, U., Brand, R. & Loidl, A. Glassy dynamics. *Contemp. Phys.* **41**, 15–36 (2000).
- Debenedetti, P. G. & Stillinger, F. H. Supercooled liquids and the glass transition. *Nature* **410**, 259–267 (2001).
- Johari, G. P. & Goldstei, M. Viscous liquids and glass transition.2. Secondary relaxations in glasses of rigid molecules. *J. Chem. Phys.* **53**, 2372–2388 (1970).
- Yu, H. B., Wang, W. H. & Samwer, K. The β relaxations in metallic glasses: an overview. *Mater. Today* **16**, 183–191 (2013).
- Ngai, K. L. & Paluch, M. Classification of secondary relaxation in glass-formers based on dynamic properties. *J. Chem. Phys.* **120**, 857–873 (2004).
- Capaccioli, S., Paluch, M., Prevosto, D., Wang, L. M. & Ngai, K. L. Many-body nature of relaxation processes in glass-forming systems. *J. Chem. Phys. Lett.* **3**, 735–743 (2012).
- Casalini, R. & Roland, C. M. Aging of the secondary relaxation to probe structural relaxation in the glassy state. *Phys. Rev. Lett.* **102**, 035701 (2009).
- Böhmer, R. *et al.* Correlation of Primary and Secondary Relaxations in a Supercooled Liquid. *Phys. Rev. Lett.* **97**, 135701 (2006).
- Ngai, K. L. Relation between some secondary relaxations and the alpha relaxations in glass-forming materials according to the coupling model. *J. Chem. Phys.* **109**, 6982–6994 (1998).
- Yu, H. B., Samwer, K., Wu, Y. & Wang, W. H. Correlation between β relaxation and self-diffusion of the smallest constituting atoms in metallic glasses. *Phys. Rev. Lett.* **109**, 095508 (2012).
- Richert, R. & Samwer, K. Enhanced diffusivity in supercooled liquids. *New J. Phys.* **9**, 36 (2007).
- Ngai, K. L. & Capaccioli, S. An explanation of the differences in diffusivity of the components of the metallic glass $\text{Pd}_{43}\text{Cu}_{27}\text{Ni}_{10}\text{P}_{20}$. *J. Phys. Chem.* **138**, 094504 (2013).
- Ngai, K. L. & Yu, H. B. Origin of ultrafast Ag radiotracer diffusion in shear bands of deformed bulk metallic glass $\text{Pd}_{40}\text{Ni}_{40}\text{P}_{20}$. *J. Appl. Phys.* **113**, 103508 (2013).
- Priestley, R. D., Ellison, C. J., Broadbent, L. J. & Torkelson, J. M. Structural relaxation of polymer glasses at surfaces, interfaces, and in between. *Science* **309**, 456–459 (2005).
- Hachenberg, J. *et al.* Merging of the α and β relaxations and aging via the Johari-Goldstein modes in rapidly quenched metallic glasses. *Appl. Phys. Lett.* **92**, 131911 (2008).
- Boyer, R. F. Dependence of mechanical properties on molecular motion in polymers. *Polym. Eng. Sci.* **8**, 161–185 (1968).
- Yu, H. B. *et al.* Tensile plasticity in metallic glasses with pronounced β relaxations. *Phys. Rev. Lett.* **108**, 015504 (2012).
- Yu, H. B., Wang, W. H., Bai, H. Y., Wu, Y. & Chen, M. W. Relating activation of shear transformation zones to β relaxations in metallic glasses. *Phys. Rev. B* **81**, 220201 (2010).
- Munch, E., Pelletier, J. M., Sixou, B. & Vigier, G. Characterization of the drastic increase in molecular mobility of a deformed amorphous polymer. *Phys. Rev. Lett.* **97**, 207801 (2006).
- Bhattacharya, S. & Suryanarayanan, R. Local mobility in amorphous pharmaceuticals—characterization and implications on stability. *J. Pharm. Sci.* **98**, 2935–2953 (2009).
- Cicerone, M. T. & Douglas, J. F. β -relaxation governs protein stability in sugar-glass matrices. *Soft Matter* **8**, 2983–2991 (2012).
- Ichitubo, T. *et al.* Microstructure of fragile metallic glasses inferred from ultrasound-accelerated crystallization in Pd-based metallic glasses. *Phys. Rev. Lett.* **95**, 245501 (2005).
- Schneider, U., Brand, R., Lunkenheimer, P. & Loidl, A. Excess wing in the dielectric loss of glass formers: a Johari-Goldstein beta relaxation? *Phys. Rev. Lett.* **84**, 5560–5563 (2000).
- Tanaka, H. Origin of the excess wing and slow beta relaxation of glass formers: a unified picture of local orientational fluctuations. *Phys. Rev. E* **69**, 021502 (2004).
- Pelletier, J. M., Van de Moortele, B. & Lu, I. R. Viscoelasticity and viscosity of Pd-Ni-Cu-P bulk metallic glasses. *Mater. Sci. Eng. A* **336**, 190–195 (2002).
- Stevenson, J. D. & Wolynes, P. G. A universal origin for secondary relaxations in supercooled liquids and structural glasses. *Nat. Phys.* **6**, 62–68 (2010).
- Wang, W. H. The elastic properties, elastic models and elastic perspectives of metallic glasses. *Prog. Mater. Sci.* **57**, 487–656 (2012).
- Ma, D. *et al.* Elastic moduli inheritance and the weakest link in bulk metallic glasses. *Phys. Rev. Lett.* **108**, 085501 (2012).
- Inoue, A. Stabilization of metallic supercooled liquid and bulk amorphous alloys. *Acta Mater.* **48**, 279–306 (2000).

34. Takeuchi, A. & Inoue, A. Classification of bulk metallic glasses by atomic size difference, heat of mixing and period of constituent elements and its application to characterization of the main alloying element. *Mater. Trans.* **46**, 2817–2829 (2005).
35. He, Q., Cheng, Y. Q., Ma, E. & Xu, J. Locating bulk metallic glasses with high fracture toughness: chemical effects and composition optimization. *Acta Mater.* **59**, 202–215 (2011).
36. Yuan, C. C., Xiang, J. F., Xi, X. K. & Wang, W. H. NMR Signature of evolution of ductile-to-brittle transition in bulk metallic glasses. *Phys. Rev. Lett.* **107**, 236403 (2011).
37. Park, E. S., Chang, H. J. & Kim, D. H. Effect of addition of Be on glass-forming ability, plasticity and structural change in Cu–Zr bulk metallic glasses. *Acta Mater.* **56**, 3120–3131 (2008).
38. Park, B. J. *et al.* Phase separating bulk metallic glass: a hierarchical composite. *Phys. Rev. Lett.* **96**, 245503 (2006).
39. Mattern, N. *et al.* Microstructure and thermal behavior of two-phase amorphous Ni–Nb–Y alloy. *Scripta Mater.* **53**, 271–274 (2005).
40. He, J. *et al.* A bridge from monotectic alloys to liquid-phase-separated bulk metallic glasses: design, microstructure and phase evolution. *Acta Mater.* **61**, 2102–2112 (2013).
41. Yang, L. *et al.* Nanoscale solute partitioning in bulk metallic glasses. *Adv. Mater.* **21**, 305–308 (2009).
42. Boer, F. R. D. *Cohesion in Metals: Transition Metal Alloys* (North-Holland, Elsevier Scientific Publishing Co., 1988).
43. Yu, H. B., Wang, Z., Wang, W. H. & Bai, H. Y. Relation between β relaxation and fragility in LaCe-based metallic glasses. *J. Non-Cryst. Solids* **358**, 869–871 (2012).
44. Cohen, Y., Karmakar, S., Procaccia, I. & Samwer, K. The nature of the β -peak in the loss modulus of amorphous solids. *Europhys. Lett.* **100**, 36003 (2012).
45. Bedorf, D. & Samwer, K. Length scale effects on relaxations in metallic glasses. *J. Non-Cryst. Solids* **356**, 340–343 (2010).
46. Mattsson, J., Bergman, R., Jacobsson, P. & Börjesson, L. Chain-length-dependent relaxation scenarios in an oligomeric glass-forming system: From merged to well-separated α and β loss peaks. *Phys. Rev. Lett.* **90**, 075702 (2003).
47. Döb, A., Paluch, M., Sillescu, H. & Hinze, G. From strong to fragile glass formers: Secondary relaxation in polyalcohols. *Phys. Rev. Lett.* **88**, 095701 (2002).
48. Ngai, K. L. An extended coupling model description of the evolution of dynamics with time in supercooled liquids and ionic conductors. *J. Phys. Condens. Matter* **15**, S1107–S1124 (2003).
49. Guan, P. F., Fujita, T., Hirata, A., Liu, Y. H. & Chen, M. W. Structural origins of the excellent glass forming ability of Pd₄₀Ni₄₀P₂₀. *Phys. Rev. Lett.* **108**, 175501 (2012).
50. Hosokawa, S. *et al.* Inhomogeneity and glass-forming ability in the bulk metallic glass Pd_{42.5}Ni_{7.5}Cu₃₀P₂₀ as seen via x-ray spectroscopies. *Phys. Rev. B* **80**, 174204 (2009).
51. Kumar, V. *et al.* Atomic and electronic structure of Pd₄₀Ni₄₀P₂₀ bulk metallic glass from ab initio simulations. *Phys. Rev. B* **84**, 134204 (2011).
52. Casalini, R., Snow, A. W. & Roland, C. M. Temperature dependence of the Johari–Goldstein relaxation in poly(methyl methacrylate) and poly(thiomethyl methacrylate). *Macromolecules* **46**, 330–334 (2012).

Acknowledgements

H.B.Y. thanks the Alexander von Humboldt Foundation for support with a post-doctoral fellowship. K.S. acknowledges the supports from the German Science Foundation within the FOR 1394 and the Leibniz-Program (Sa 337/10-1). W.H.W. and H.Y.B. acknowledge the supports from NSF of China (51271195).

Author contributions

H.B.Y. initiated the research and conducted the experiments with W.H.W. and H.Y.B. The mechanism was conceived by K.S. H.B.Y. and K.S. analysed the results and wrote the manuscript.

Additional information

Competing financial interests: The authors declare no competing financial interests.

Reprints and permission information is available online at <http://npg.nature.com/reprintsandpermissions/>

How to cite this article: Yu, H. B. *et al.* Chemical influence on β -relaxations and the formation of molecule-like metallic glasses. *Nat. Commun.* **4**:2204 doi: 10.1038/ncomms3204 (2013).